

ICC Evaluation Service, Inc.
www.icc-es.org

Business/Regional Office ■ 5360 Workman Mill Road, Whittier, California 90601 ■ (562) 699-0543
Regional Office ■ 900 Montclair Road, Suite A, Birmingham, Alabama 35213 ■ (205) 599-9800
Regional Office ■ 4051 West Flossmoor Road, Country Club Hills, Illinois 60478 ■ (708) 799-2305

DIVISION: 06—WOOD AND PLASTICS
Section: 06180—Glued-Laminated Construction

REPORT HOLDER:

ROSBORO LUMBER COMPANY
POST OFFICE BOX 20
SPRINGFIELD, OREGON 97477
(541) 746-8411
www.rosboro.com

EVALUATION SUBJECT:

ROSBORO BIGBEAM GLUED-LAMINATED BEAMS

1.0 EVALUATION SCOPE

Compliance with the following codes:

- 2003 *International Building Code*® (IBC)
- 2003 *International Residential Code*® (IRC)
- BOCA® *National Building Code*/1999 (BNBC)
- 1999 *Standard Building Code*® (SBC)
- 1997 *Uniform Building Code*™ (UBC)

Properties evaluated:

Structural

2.0 USES

The Rosboro BigBeam 2.4E and BigBeam 2.2E are glued-laminated beams for use as structural components in buildings where combustible construction is permitted.

3.0 DESCRIPTION

3.1 General:

The BigBeam 2.4E and BigBeam 2.2E Glued-laminated Beams are fabricated with layup combinations identified as 33F-2.4E and 30F-2.2E, respectively. The combinations are balanced and consist of E-rated southern pine (SP) lumber, with laminated veneer lumber (LVL) used as outer laminations. Individual beam laminations are 2 inches (51 mm) or less in net thickness. Beam widths are between 2¹/₂ and 10 inches (64 and 254 mm) and beam depths are between 9¹/₄ and 30 inches (235 to 762 mm).

3.2 Materials:

3.2.1 Adhesives: The face and end joint bonding adhesives comply with ASTM D 2559 for exterior wet use.

3.2.2 End Joints: The end joints comply with quality control requirements of ANSI/AITC A190.1 and APA—The Engineered Wood Association.

3.2.3 Laminating Stock: The beams are manufactured using E-rated lumber laminations having known ultimate tensile strength and plank MOE values, and with outer LVL laminations received and tested under a quality control program outlined in the manufacturer's approved quality control manual and recognized in ICC-ES legacy report ER-5598.

3.3 Layup:

Manufacturing grade, layup requirements and design for the grade combinations of lumber/LVL described in this report comply with the design parameters specified in the ICC-ES evaluation report addressing the APA—The Engineered Wood Association's "GAP2005" software (ESR-1940), and are included in the plant production procedures specified in the approved quality control manual.

4.0 DESIGN

Design stress values are listed in Table 1, and are for beams having six or more laminations stressed primarily in bending due to loads applied perpendicular to the wide faces of the laminations. Design and installation requirements for structural glued-laminated beams and connections shall comply with the applicable code.

5.0 CONDITIONS OF USE

The BigBeam 2.4E and BigBeam 2.2E Glued-laminated Beams described in this report comply with, or are suitable alternatives to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions:

- 5.1** The allowable design stresses determined from the GAP2005 computer program are limited to those layup combinations shown in Table 1. Design stresses for normal conditions of loading must not exceed those set forth in Table 1.
- 5.2** The design stresses for combinations, as noted in Table 1, are for members with six or more laminations stressed primarily in bending due to loads applied perpendicular to the wide faces of the laminations.
- 5.3** Design calculations, signed and sealed by a registered design professional, verifying compliance with this report and the design requirements of the applicable code, must be submitted to the code official for approval.
- 5.4** The effects of checking of the wood members are outside the scope of this report.
- 5.5** The BigBeam 2.4E and BigBeam 2.2E Glued-laminated Beams are manufactured in Springfield, Oregon, under a quality control program with inspections by APA—The Engineered Wood Association (AA-649).

6.0 EVIDENCE SUBMITTED

- 6.1 Design calculations of allowable stresses as determined by the GAP2005 computer program in accordance with ASTM D 3737.
- 6.2 Qualification testing data in accordance with ANSI/AITC A190.1.
- 6.3 A quality control manual, dated August 7, 2006.

7.0 IDENTIFICATION:

The BigBeam 2.4E and BigBeam 2.2E Glued-laminated Beams are identified by a stamp bearing the name of Rosboro Lumber Company; the manufacturing plant number (#1001) or address; the glulam combination identification; the evaluation report number (ESR-1937); and the name of the inspection agency (APA—The Engineered Wood Association).

TABLE 1—DESIGN VALUES FOR ROSBORO BIGBEAM™ STRUCTURAL GLUED-LAMINATED TIMBER FOR NORMAL DURATION OF LOAD AND DRY CONDITIONS⁽¹⁾

Symbol	Species ⁽²⁾ Outer/Core	Bending About X-X Axis (Loaded Perpendicular to Wide Faces of Laminations)					Bending About Y-Y Axis (Loaded Parallel to Wide Faces of Laminations)					Axially Loaded		Fasteners		
		Extreme Fiber in Bending ⁽³⁾		Compression Perpendicular to Grain ⁽⁴⁾		Shear Parallel to Grain ⁽⁵⁾	Modulus of Elasticity ⁽⁶⁾	Extreme Fiber in Bending ⁽³⁾	Compr. Perpendicular to Grain ⁽⁴⁾	Shear Parallel to Grain ⁽⁵⁾	Modulus of Elasticity ⁽⁶⁾	Tension Parallel to Grain	Compr. Parallel to Grain	Modulus of Elasticity	Specific Gravity for Dowel-Type Fastener Design	
		Tension Zone Stressed in Tension	Compr. Zone Stressed in Tension	Tension Face	Compr. Face										Top or Bottom Face	Side Face
		F _{bx} ⁺ (psi)	F _{bx} ⁻ (psi)	F _{cx} ^{ax} (psi)	F _{vx} (psi)	E _x (10 ⁶ psi)	F _{bx} ⁺ (psi)	F _{bx} ⁻ (psi)	F _{cy} (psi)	E _y (10 ⁶ psi)	F _t (psi)	F _c (psi)	E _{axial} (10 ⁶ psi)	SG		
Rosboro BigBeam™ 2.4E	LVL/SP	3300	3300	650	300	2.4	1900	650	265	1.7	1300	1850	1.8	0.50	0.50	
Rosboro BigBeam™ 2.2E	LVL/SP	3000	3000	650	300	2.2	1750	650	265	1.7	1250	1750	1.8	0.50	0.50	

For S1: 1 inch = 25.4 mm; 1 foot = 304.8 mm; 1 plf = 14.6 N/m; 1 psi = 6.89 kPa.

¹The tabulated design values are for normal duration of loading. For other durations of loading, see the applicable building code.

²SP = Southern pine; LVL = laminated veneer lumber per the manufacturing standard.

³The values of F_{bx} are based on members 5-1/8 inches in width by 12 inches in depth by 21 feet in length. For members with a larger volume, F_{bx} shall be multiplied by a volume factor, C_v, determined in accordance with applicable building code using 1/10 as the exponent. The beam depths are limited to 9-1/4 to 30 inches.

⁴The values of F_{cx,ax} shall be permitted to be increased to the published allowable compressive stress perpendicular to grain of the outermost laminated veneer lumber in the plank (flatwise) orientation.

⁵For non-prismatic members, members subject to impact or cyclic loading, or shear design of bending members at connections, the F_{vx} and F_{vy} values shall be multiplied by a factor of 0.72.

⁶For uniformly loaded simple-span beams, deflection is calculated as follows:

$$\delta = \frac{270 wL^4}{Ebht^3} + \frac{28.8 wL^2}{Ebht}$$

- where
- δ = deflection (in.),
 - w = applied uniform loads (lbf/ft),
 - L = design span (ft),
 - E = tabulated modulus of elasticity (lbf/in.²),
 - b = beam width (in.), and
 - h = beam depth (in.)

⁷The values of F_{by} are based on members 12 inches in depth. For depths other than 12 inches, F_{by} shall be increased by multiplying by the size factor, (12/d)^{1/8}, where d is the beam depth in inches. When d is less than 3 inches, use the size adjustment factor for 3 inches.